



FLOCK ADHESIVE 1820




RECOMMENDED FABRICS
100% Cotton
50/50 or 100% Polyester




INK APPLICATION
Flock Adhesive 1820 must be mixed with the 900 Catalyst before printing.



ADDITIVES
Not recommended



SCREEN MESH
86-110 t/in (34-43t/cm)
monofilament recommended.



EMULSION
Any direct or indirect solvent resistant emulsion or capillary film.



SQUEEGEE
60-75 Durometer
Sharp edge.



CURE TEMPERATURES
325°F (163°C) entire ink film.



CLEAN-UP
Any environment friendly plastisol type screen wash



PRODUCT PACKAGING
Quart, 1 gallon, 5 gallon containers



STORAGE OF INK CONTAINERS
65° to 90°F (18°C to 32°C). Avoid storage in direct sunlight. Keep containers well sealed



SDS
Refer to SDS prior to use

FEATURES

AXEON™ Flock Adhesive 1820 is a two-part flock adhesive used to produce high quality flock prints.

Flock Adhesive 1820 provides excellent adhesion to most flock fibers and produces a very soft and flexible flock print when the product is properly printed and cured.

Designs made with Flock Adhesive 1820 may be applied to light or dark fabrics.

SPOT FLASHING

This product will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should be dry just to the touch, with no lift off, but not totally fused. Totally fusing the underprint may cause inter-coat adhesion problems with the inks printed on top. Final fusing or curing will occur in the dryer. Failure to fuse ink properly may cause cracking, poor adhesion and poor wash fastness.

FLOCK APPLICATION

AXEON™ Flock Adhesive 1820 must be mixed with the 900 Catalyst before printing. Catalyst is provided in 2 oz. and 8 oz. containers and should be thoroughly hand stirred into the ink to the following proportions:

20 parts ink to 1 part catalyst (5% by weight)

1 oz. Catalyst to 1 pint of ink
2 oz. Catalyst to 1 quart of ink
8 oz. Catalyst to 1 gallon of ink

Ink may be used immediately after mixing. Pot life of mixed ink is 4 to 8 hours. Do not mix more ink than is needed for a job. Do not under catalyze the ink. Over catalyzation will shorten pot life of ink.

1. Stir or mix the 1820 Flock Adhesive before each use.
2. Make sure that the 1820 Flock Adhesive is kept more on the surface of the fabric when printing in order to help insure a maximum adhesive surface for the flock fibers to bond to.
3. Immediately after printing the 1820 Flock Adhesive, apply the flock fibers to the wet adhesive using the proper electrostatic flocking equipment.
4. The properly cured flock print should be vacuumed to remove excess flock fibers that have not attached themselves to the flock adhesive.

IMPORTANT INFORMATION

The optimum time/temperature cycle will vary with the amount of ink deposited, fabric and the type of heat source used. Test dryer temperatures and wash test printed product before and during a production run. Always check for possible dye migration when printing fabrics that contain polyester fibers. Always test print fabric before beginning a production run.

This ink and those in the AXEON™ product line are not formulated with PVC resins or phthalate plasticizers, nor are they intentionally added.

Care should be taken to not cross-contaminate the AXEON™ products with PVC or phthalates containing products.

Do not use standard plastisol curable reducers with this or any of the AXEON™ products.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 1600002